

ADINGPOKS AKVA 1B

Two-component water based epoxy coating for protection of concrete surfaces exposed to mechanical and chemical aggression.

Compliant to EN 1504-2: 1.3(C); 2.2(C); 5.1(C); 6.1(C); 8.2(C)

FIELD OF APLICATION

Epoxy coloured coating for protective and decorative finish of concrete wall surfaces and ceiling surfaces made of concrete in: tunnels, laboratories, storage rooms, hospitals, schools, shopping centers, etc. It is recommended as final coating for rooms, where high hygiene standards are required, in case of chemical aggression, etc. For finish treatment of the concrete for traffic, rail and hydro-technical tunnels, this coating provides a high degree of protection from carbonization, ice, salt and abrasion.

PROPERTIES

- High carbonation protection;
- Watertight;
- Vapor-permeable;
- Chemical resistance to thinned acids, alkaline, salt solutions and mineral oil;
- Excellent adhesion to substrate;
- Abrasive resistance
- Mechanical resistance;
- Non-toxic when cured;
- Bacteriologically resistant;
- Easy to apply with a paint roller or by spraying;
- Easy to maintain;

TECHNICAL FEATURES

PROPERTY	METHOD	DECLARED VALUE
Appearance		White paste
Adhesion strength (bond)	EN 1542	≥ 2,0MPa
Capilary absorbtion and permability to water		w≤0,1kg/m²h ^{1/2}
Permeability to water vapor	ISO 7783	class I Sd<5 m
Permeability to CO ₂		Sd>50m
Abrasion resistance (CS 17)		< 3000mg
Resistance to impact	EN ISO 6272-1	class II ≥10Nm
Resistance to strong chemical aggression (gasoline, diesel, engine oil, 10% CH3COOH, 20% H2SO4, 20% NaOH, 20% NaCl)	EN 13529	class I, reduction of shore hardnes ≤50%
Tough dry (at 25 °C)		24 h
Pot life (at 20 °C)		approx. 90 min.
Reaction to fire		Euroclass B -s1, d0

METHOD STATEMENT:

The concrete substrate should be sound, dry, clean, grease-free dust free, and it should be protected from water penetration and negative hydrostatic pressure and protected from vapor condensation. The humidity in the concrete substrate should be lower than 7%. For application on porous substrates, we recommend precoating with water based epoxy primer Adingpoks Akva Primer, water based epoxy coating Adingpoks Akva or material for hydrophobic impregnation Fasil V. Application can be done manually by using a paint roller, or by air-less pump.

Page 1 of 3







New concrete substrate

The substrate should be older than 28 days with minimal compressive strength of 25 MPa with humidity lower than 7%. Stains of paint and grease must be removed.

Old concrete substrate

Clean and sound substrate are the main preconditions for achieving proper adhesion. Mortar residues and other forms of dirt should be removed by mechanical or chemical means. Any damage should be repaired using appropriate materials for structural reparation.

Old epoxy substrate

The substrate should be soft machine grinded with sandpaper and cleaned.

APPLICATION

The material is prepared by separately mixing components (2-3min) with a slow electric mixer and then adding A component to B component and mixing them together at max. speed of 400 rpm. until a completely uniform mixture is obtained. If necessary, the material can be diluted with 5-10% water. The application should be in accordance with the pot life of the material, approx. 90 min.

The material can be applied manually by using paint brush, roller, or by air-less pump in two or three layers. The next layers should be applied after hardened first layer, i.e after 4-24h at ambient temperature of 10-35 °C and relative humidity less than 70%. Maximal thickness of wet film of one layer should be $200-300\mu m$, otherwise can come to sagging of the material. Declared values of the material for protection of concrete are examined at dry film thickness of $140 \mu m$.

CONSUMPTION

Adingpoks Akva 1B, for one layer: 0.15 to 0.30 kg/m² Adingpoks Akva 1B, for two layer: 0.35 to 0.60 kg/m²

CLEANING:

The tools and equipment should be cleaned with water immediately after use.

PACKAGING

The product is two component. Mixing ratio is specified on the packaging and depends from required colour and reflection.

STORAGE

In the original closed packaging, in dry premises, at temperature between 10°C and 35°C, protected from direct sunlight and freezing temperatures.

Shelf life: 9 months.

STANDARD COLOR

RAL 9003

Page 2 of 3





CE MARKING

(6

2032

ADING AD Skopje,

Novoselski pat (ul.1409) No.11, 1060 Skopje, North Macedonia

19

GOAC0XX/2

EN 1504-2 : 2004

ADINGPOKS AKVA 1B

Two component water based epoxy coating for concrete ingress protection and for increasing physical and chemical resistance

Permeability to CO2	Sd > 50 m	
Permeability to water vapour	Class I , Sd ≤ 5 m	
Capillary absorption and permeability to water	$\leq 0.1 \text{ kg/m}^2 \cdot h^{0,5}$	
Adhesion strength by pull-off test	≥ 2,0 N/mm ²	
Impact resistance	Class II≥ 10 N/m , no cracks, no delamination	
Abrasion resistance	< 3000 mg	
Resistance to severe chemical attack	Class I: 3 days without pressure ≤ 50 % reduction in Shore hardness after treatment in test liquids: petrol; diesel and motor oil; 10 % CH ₃ COOH; 20 % H ₂ SO ₄ ;20% NaOH; 20% NaCl	
Reaction to fire	Класа B – s1, d0	
Dangerous substances	No performance determined	

Health hazards: Avoid contact of the product with skin and eyes and avoid direct inhalation when mixing the components. In case of accidental contact with skin, remove it immediately by using a dry towel or a towel lightly soaked in water, and then wash the skin thoroughly with clean water and soap. If the material splashes into the eyes, immediately rinse the eyes with clean water and seek medical attention. Additional information are provided in the Safety Data Sheet of the product.

Fire: Ensure ventilation of the premises where epoxy resins are handled.

<u>Cleaning and disposal:</u> Loose residues of Adingpoks Akva 1B should be cleaned with water. The old and used packaging should be disposed of in accordance with local rules and regulations for that type of waste. We recommend that the method of application and the necessary quantities should be adjusted to the conditions on site, as well as mandatory use of appropriate equipment.

Page 3 of 3



